



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Ferme Criadorable
177 Chemin Poulin, Dudswell
QC JOB 1GO, Canada

Date: 24-Jun-24
Shear ID: 262527
Test No: 618940


Animal and Sample Description

Animal Name: Ariya Beleni's Azimut
Registry #: 36199365
Breed: Huacaya
Sex: Male
Colour: 100 - White

Date of Birth (Age): 27-Aug-18
Sample Location: GRID
Sample Date: 24-May-24
Previous Shear Date: 20-May-23
Total Fleece Wt (lbs):

Laboratory Data

Mean Fiber Diameter:	17.3 microns	Mean Staple Length:	82 mm
Standard Deviation:	3.7 microns	Length Standard Deviation:	3.0 mm
Coefficient of Variation:	21.2 %	Length Coefficient of Variation:	3.7 %
Spin Fineness:	16.8 microns	Mean Curvature:	68.6 deg/mm
Fibers Greater Than 30 microns:	0.8 %	SD Curvature:	43.3 deg/mm
Comfort Factor:	99.2 %	Medullated Fibers:	2.0 %



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilmorie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com