



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Ferme Criadorable
177 Chemin Poulin, Dudswell
QC JOB 1GO, Canada

Date: 24-Jun-24
Shear ID:
Test No: 618926


Animal and Sample Description

Animal Name: Criadorable Perseide
Registry #:
Breed: Huacaya
Sex: Female
Colour: 100 - White

Date of Birth (Age): 12-Aug-18
Sample Location:
Sample Date: 25-May-24
Previous Shear Date:
Total Fleece Wt (lbs):

Laboratory Data

Mean Fiber Diameter:	21.7 microns	Comfort Factor:	95.6 %
Standard Deviation:	4.9 microns	Mean Curvature:	50.6 deg/mm
Coefficient of Variation:	22.4 %	SD Curvature:	34.8 deg/mm
Spin Fineness:	21.4 microns	Medullated Fibers:	4.7 %
Fibers Greater Than 30 microns:	4.4 %		



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilbirnie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com