



## Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Nancy Bouchard  
177 Chemin Poulin, Dudswell  
QC J0B 1G0, CA

Date: 23-May-24  
Shear ID:  
Test No: 618463


### Animal and Sample Description

Animal Name: Criadorable Hope  
Registry #: CAN49140  
Breed: Huacaya  
Sex: Female  
Colour: 201 - Beige

Date of Birth (Age): 3-Jun-19  
Sample Location:  
Sample Date: 21-May-22  
Previous Shear Date:  
Total Fleece Wt (lbs):

### Laboratory Data

Mean Fiber Diameter:	15.0 microns	Comfort Factor:	99.7 %
Standard Deviation:	3.3 microns	Mean Curvature:	50.0 deg/mm
Coefficient of Variation:	21.9 %	SD Curvature:	38.1 deg/mm
Spin Fineness:	14.7 microns	Medullated Fibers:	1.9 %
Fibers Greater Than 30 microns:	0.3 %		



### Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear  
Business Manager

Ioasa Kosena  
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilbirnie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: [WoolOnline@sgs.com](mailto:WoolOnline@sgs.com) Web: [www.wooltesting.sgs.com](http://www.wooltesting.sgs.com)