



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Ferme Criadorable
177 Chemin Poulin, Dudswell
QC JOB 1GO, Canada

Date: 24-Jun-24
Shear ID:
Test No: 618929


Animal and Sample Description

Animal Name: Criadorable Boule de coton
Registry #:
Breed: Huacaya
Sex: Male
Colour: 100 - White

Date of Birth (Age): 30-Jun-20
Sample Location:
Sample Date: 25-May-24
Previous Shear Date:
Total Fleece Wt (lbs):

Laboratory Data

Mean Fiber Diameter:	17.3 microns	Comfort Factor:	99.5 %
Standard Deviation:	3.8 microns	Mean Curvature:	57.0 deg/mm
Coefficient of Variation:	21.7 %	SD Curvature:	37.4 deg/mm
Spin Fineness:	17.0 microns	Medullated Fibers:	2.2 %
Fibers Greater Than 30 microns:	0.5 %		



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilmorie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com