



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Nancy Bouchard
177 Chemin Poulin, Dudswell
QC J0B 1G0, CA

Date: 23-May-24
Shear ID:
Test No: 618483


Animal and Sample Description

Animal Name: Criadorable Belle
Registry #:
Breed: Huacaya
Sex: Female
Colour: 100 - White

Date of Birth (Age): 22-Aug-20
Sample Location: GRID
Sample Date: 20-May-23
Previous Shear Date:
Total Fleece Wt (lbs):

Laboratory Data

Mean Fiber Diameter:	23.0 microns	Mean Staple Length:	101 mm
Standard Deviation:	5.0 microns	Length Standard Deviation:	3.3 mm
Coefficient of Variation:	21.5 %	Length Coefficient of Variation:	3.2 %
Spin Fineness:	22.5 microns	Mean Curvature:	43.9 deg/mm
Fibers Greater Than 30 microns:	7.6 %	SD Curvature:	34.2 deg/mm
Comfort Factor:	92.4 %	Medullated Fibers:	11.1 %



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilbirnie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com