



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Ferme Criadorable
177 Chemin Poulin, Dudswell
QC JOB 1GO, Canada

Date: 24-Jun-24
Shear ID:
Test No: 618927


Animal and Sample Description

Animal Name: Criadorable Adalyne
Registry #:
Breed: Huacaya
Sex: Female
Colour: 100 - White

Date of Birth (Age): 3-Sep-21
Sample Location:
Sample Date: 25-May-24
Previous Shear Date:
Total Fleece Wt (lbs):

Laboratory Data

Mean Fiber Diameter:	19.4 microns	Comfort Factor:	98.4 %
Standard Deviation:	4.2 microns	Mean Curvature:	54.9 deg/mm
Coefficient of Variation:	21.7 %	SD Curvature:	35.8 deg/mm
Spin Fineness:	19.0 microns	Medullated Fibers:	5.8 %
Fibers Greater Than 30 microns:	1.6 %		



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilbirnie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com