



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Ferme Criadorable
177 Chemin Poulin, Dudswell
QC JOB 1GO, Canada

Date: 24-Jun-24
Shear ID: 262529
Test No: 618942


Animal and Sample Description

Animal Name: Criadorable Negan
Registry #: 35138716
Breed: Huacaya
Sex: Male
Colour: 202 - Light Fawn

Date of Birth (Age): 14-Jul-21
Sample Location: GRID
Sample Date: 24-May-24
Previous Shear Date: 20-May-23
Total Fleece Wt (lbs):

Laboratory Data

Mean Fiber Diameter:	16.6 microns	Mean Staple Length:	82 mm
Standard Deviation:	3.7 microns	Length Standard Deviation:	2.5 mm
Coefficient of Variation:	21.9 %	Length Coefficient of Variation:	3.0 %
Spin Fineness:	16.3 microns	Mean Curvature:	60.4 deg/mm
Fibers Greater Than 30 microns:	0.6 %	SD Curvature:	40.7 deg/mm
Comfort Factor:	99.4 %	Medullated Fibers:	3.5 %



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilbirnie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com