



## Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Ferme Criadorable  
177 Chemin Poulin, Dudswell  
QC JOB 1GO, Canada

Date: 24-Jun-24  
Shear ID:  
Test No: 618933


### Animal and Sample Description

Animal Name: Criadorable Dwight  
Registry #:  
Breed: Huacaya  
Sex: Male  
Colour: 100 - White

Date of Birth (Age): 9-Jul-22  
Sample Location:  
Sample Date: 25-May-24  
Previous Shear Date:  
Total Fleece Wt (lbs):

### Laboratory Data

Mean Fiber Diameter:	18.8 microns	Comfort Factor:	99.1 %
Standard Deviation:	3.8 microns	Mean Curvature:	53.4 deg/mm
Coefficient of Variation:	20.4 %	SD Curvature:	37.8 deg/mm
Spin Fineness:	18.2 microns	Medullated Fibers:	2.0 %
Fibers Greater Than 30 microns:	0.9 %		



### Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear  
Business Manager

Ioasa Kosena  
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilbirnie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: [WoolOnline@sgs.com](mailto:WoolOnline@sgs.com) Web: [www.wooltesting.sgs.com](http://www.wooltesting.sgs.com)