



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Ferme Criadorable
177 Chemin Poulin, Dudswell
QC JOB 1GO, Canada

Date: 24-Jun-24
Shear ID:
Test No: 618923


Animal and Sample Description

Animal Name: Criadorable Alden
Registry #:
Breed: Huacaya
Sex: Male
Colour: 204 - Medium Fawn

Date of Birth (Age): 30-Jun-22
Sample Location:
Sample Date: 25-May-24
Previous Shear Date:
Total Fleece Wt (lbs):

Laboratory Data

Mean Fiber Diameter:	16.9 microns	Comfort Factor:	99.3 %
Standard Deviation:	3.2 microns	Mean Curvature:	52.0 deg/mm
Coefficient of Variation:	18.9 %	SD Curvature:	35.1 deg/mm
Spin Fineness:	16.2 microns		
Fibers Greater Than 30 microns:	0.7 %		



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilmorie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com