



## Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Ferme Criadorable  
177 Chemin Poulin, Dudswell  
QC JOB 1GO, Canada

Date: 24-Jun-24  
Shear ID:  
Test No: 618935

### Animal and Sample Description


Animal Name: Criadorable Wes  
Registry #:  
Breed: Huacaya  
Sex: Male  
Colour: 209 - Light Brown

Date of Birth (Age): 10-Aug-23  
Sample Location:  
Sample Date: 25-May-24  
Previous Shear Date:  
Total Fleece Wt (lbs):

### Laboratory Data

Mean Fiber Diameter: 17.1 microns  
Standard Deviation: 3.8 microns  
Coefficient of Variation: 22.5 %  
Spin Fineness: 16.9 microns  
Fibers Greater Than 30 microns: 1.1 %

Comfort Factor: 98.9 %  
Mean Curvature: 48.9 deg/mm  
SD Curvature: 35.3 deg/mm



### Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear  
Business Manager

Ioasa Kosena  
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilmorie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: [WoolOnline@sgs.com](mailto:WoolOnline@sgs.com) Web: [www.wooltesting.sgs.com](http://www.wooltesting.sgs.com)