



## Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Alpacas Bibar Ranch  
8720 Moss Rock Rd, Colorado Springs  
CO 80908, US

Date: 2-Oct-24  
Shear ID: 264757  
Test No: 621408


### Animal and Sample Description

Animal Name: BIR's Hermes  
Registry #: 36196210  
Breed: Suri  
Sex: Male  
Colour: 202 - Light Fawn

Date of Birth (Age): 24-Jun-23  
Sample Location: GRID  
Sample Date: 8-Jun-24  
Previous Shear Date: 25-Jun-23  
Total Fleece Wt (lbs):

### Laboratory Data

Mean Fiber Diameter:	24.8 microns	Mean Staple Length:	178 mm
Standard Deviation:	4.8 microns	Length Standard Deviation:	21.8 mm
Coefficient of Variation:	19.4 %	Length Coefficient of Variation:	12.3 %
Spin Fineness:	23.9 microns	Mean Curvature:	23.7 deg/mm
Fibers Greater Than 30 microns:	10.8 %	SD Curvature:	29.1 deg/mm
Comfort Factor:	89.2 %	Medullated Fibers:	6.6 %



### Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear  
Business Manager

Ioasa Kosena  
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilbirnie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: [WoolOnline@sgs.com](mailto:WoolOnline@sgs.com) Web: [www.wooltesting.sgs.com](http://www.wooltesting.sgs.com)