



WINDY'S JETT

AFD: 16.4 μ
SD: 3.0 μ
CV: 18.6 %
CF: 100.0 %
Curve: 29.7 Dg/mm
Min: 16.2 μ
Max: 18.3 μ
Staple: 65.0 mm



WINDY'S JETT

AFD: 16.4 μ
SD: 3.0 μ
CV: 18.6 %
CF: 100.0 %
Curve: 29.7 Dg/mm
Min: 16.2 μ
Max: 18.3 μ
Staple: 65.0 mm



Alpaca Fiber Testing USA