


AFD: 26.0 μ
SD: 5.6 μ
CV: 21.4 %
CF: 81.5 %
Curve: 15.8 Dg/mm
Min: 24.6 μ
Max: 28.1 μ
Staple: 115.0 mm

% of Fibers




Alpaca Fiber Testing USA

Fiber Diameter (microns)

RHIANNON

AFD: 26.0 μ
SD: 5.6 μ
CV: 21.4 %
CF: 81.5 %
Curve: 15.8 Dg/mm
Min: 24.6 μ
Max: 28.1 μ
Staple: 115.0 mm



Alpaca Fiber Testing USA