


TSS AVA'S LANTANA ET

AFD: 24.2 μ
SD: 5.3 μ
CV: 22.1 %
CF: 87.8 %
Curve: 12.2 Dg/mm
Min: 23.4 μ
Max: 25.8 μ
Staple: 135.0 mm

% of Fibers



Alpaca Fiber Testing USA

Fiber Diameter (microns)

TSS AVA'S LANTANA ET

AFD: 24.2 μ
SD: 5.3 μ
CV: 22.1 %
CF: 87.8 %
Curve: 12.2 Dg/mm
Min: 23.4 μ
Max: 25.8 μ
Staple: 135.0 mm

