


TIKANUI'S HANDSOME JACK

AFD: 22.3 μ
SD: 4.6 μ
CV: 20.5 %
CF: 94.3 %
Curve: 15.8 Dg/mm
Min: 21.9 μ
Max: 26.5 μ
Staple: 140.0 mm

% of Fibers



Alpaca Fiber Testing USA

Fiber Diameter (microns)

TIKANUI'S HANDSOME JACK

AFD: 22.3 μ
SD: 4.6 μ
CV: 20.5 %
CF: 94.3 %
Curve: 15.8 Dg/mm
Min: 21.9 μ
Max: 26.5 μ
Staple: 140.0 mm

