



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Sandollar Llc + Appraisal Group Sewa
2001 S Washington St. #104, Kennewick
WA 99337, USA

Date: 7-Sep-21
Shear ID: 223971
Test No: 604588


Animal and Sample Description

Animal Name: SDAF Sniper's Sarah
Registry #: 35503279
Breed: Suri
Sex: Female
Colour: 410 - Dark Brown

Date of Birth (Age): 1-Jun-19
Sample Location: GRID
Sample Date: 24-May-21
Previous Shear Date: 24-May-20
Total Fleece Wt (lbs):

Laboratory Data

| | | | |
|---------------------------------|--------------|----------------------------------|-------------|
| Mean Fiber Diameter: | 26.9 microns | Mean Staple Length: | 139 mm |
| Standard Deviation: | 7.8 microns | Length Standard Deviation: | 20.6 mm |
| Coefficient of Variation: | 29.1 % | Length Coefficient of Variation: | 14.8 % |
| Spin Fineness: | 28.2 microns | Mean Curvature: | 28.2 deg/mm |
| Fibers Greater Than 30 microns: | 20.1 % | SD Curvature: | 12.1 deg/mm |
| Comfort Factor: | 79.9 % | | |



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilmorie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com