



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Blazing Star Ranch
3424 S Broadway, Englewood
CO 80113-2529, US

Date: 2-Oct-24
Shear ID: 268846
Test No: 621531


Animal and Sample Description

Animal Name: LDR XANDER
Registry #: 35321958
Breed: Huacaya
Sex: Male
Colour: 211 - Medium Rose Grey

Date of Birth (Age): 1-Jul-17
Sample Location: GRID
Sample Date: 12-May-24
Previous Shear Date: 3-Jun-23
Total Fleece Wt (lbs): 10.05

Laboratory Data

Mean Fiber Diameter:	24.5 microns	Mean Staple Length:	85 mm
Standard Deviation:	5.8 microns	Length Standard Deviation:	2.2 mm
Coefficient of Variation:	23.6 %	Length Coefficient of Variation:	2.6 %
Spin Fineness:	24.4 microns	Mean Curvature:	41.5 deg/mm
Fibers Greater Than 30 microns:	13.0 %	SD Curvature:	32.2 deg/mm
Comfort Factor:	87.0 %		



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilmorie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com