



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Red Granites Ranch
1021 Red Granite Ranch Rd, Livermore
CO 80536, US

Date: 26-Sep-24
Shear ID: 264232
Test No: 621226


Animal and Sample Description

Animal Name: RED GRANITES PENDRAGON BY ALYD.
Registry #: 35547419
Breed: Huacaya
Sex: Male
Colour: 204 - Medium Fawn

Date of Birth (Age): 13-Aug-22
Sample Location: GRID
Sample Date: 31-May-24
Previous Shear Date: 3-Jun-23
Total Fleece Wt (lbs): 7.125

Laboratory Data

Mean Fiber Diameter:	20.6 microns	Mean Staple Length:	103 mm
Standard Deviation:	4.0 microns	Length Standard Deviation:	3.4 mm
Coefficient of Variation:	19.2 %	Length Coefficient of Variation:	3.3 %
Spin Fineness:	19.7 microns	Mean Curvature:	57.6 deg/mm
Fibers Greater Than 30 microns:	1.2 %	SD Curvature:	40.3 deg/mm
Comfort Factor:	98.8 %		



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilmorie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com