



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Red Granites Ranch
1021 Red Granite Ranch Rd, Livermore
CO 80536, US

Date: 26-Sep-24
Shear ID: 264245
Test No: 621239


Animal and Sample Description

Animal Name: RED GRANITES PRINCE CASPIAN
Registry #: 35574927
Breed: Huacaya
Sex: Male
Colour: 360 - Bay Black

Date of Birth (Age): 4-Jun-22
Sample Location: GRID
Sample Date: 31-May-24
Previous Shear Date: 3-Jun-23
Total Fleece Wt (lbs): 7.375

Laboratory Data

Mean Fiber Diameter:	21.4 microns	Mean Staple Length:	105 mm
Standard Deviation:	4.6 microns	Length Standard Deviation:	4.0 mm
Coefficient of Variation:	21.6 %	Length Coefficient of Variation:	3.8 %
Spin Fineness:	20.9 microns	Mean Curvature:	50.8 deg/mm
Fibers Greater Than 30 microns:	3.2 %	SD Curvature:	38.0 deg/mm
Comfort Factor:	96.8 %		



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilmorie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com