



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Red Granites Ranch
1021 Red Granite Ranch Rd, Livermore
CO 80536, US

Date: 25-Sep-24
Shear ID: 264302
Test No: 621295


Animal and Sample Description

Animal Name: RED GRANITES VASTEEN
Registry #: 35547105
Breed: Huacaya
Sex: Male
Colour: 100 - White

Date of Birth (Age): 13-Sep-22
Sample Location: GRID
Sample Date: 31-May-24
Previous Shear Date: 3-Jun-23
Total Fleece Wt (lbs): 6.25

Laboratory Data

Mean Fiber Diameter:	17.7 microns	Mean Staple Length:	112 mm
Standard Deviation:	3.4 microns	Length Standard Deviation:	3.0 mm
Coefficient of Variation:	19.4 %	Length Coefficient of Variation:	2.6 %
Spin Fineness:	17.0 microns	Mean Curvature:	50.6 deg/mm
Fibers Greater Than 30 microns:	0.5 %	SD Curvature:	38.1 deg/mm
Comfort Factor:	99.5 %	Medullated Fibers:	2.3 %



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilmorie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com