



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Red Granites Ranch
1021 Red Granite Ranch Rd, Livermore
CO 80536, US

Date: 26-Sep-24
Shear ID: 266184
Test No: 621329


Animal and Sample Description

Animal Name: RED GRANITES RGR VENUS
Registry #: 35547136
Breed: Huacaya
Sex: Female
Colour: 204 - Medium Fawn

Date of Birth (Age): 4-Sep-22
Sample Location: GRID
Sample Date: 31-May-24
Previous Shear Date: 3-Jun-23
Total Fleece Wt (lbs): 4.375

Laboratory Data

Mean Fiber Diameter:	20.3 microns	Mean Staple Length:	101 mm
Standard Deviation:	3.7 microns	Length Standard Deviation:	10.3 mm
Coefficient of Variation:	18.3 %	Length Coefficient of Variation:	10.3 %
Spin Fineness:	19.3 microns	Mean Curvature:	58.2 deg/mm
Fibers Greater Than 30 microns:	0.9 %	SD Curvature:	41.3 deg/mm
Comfort Factor:	99.1 %		



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilmorie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com