



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Red Granites Ranch
1021 Red Granite Ranch Rd, Livermore
CO 80536, US

Date: 25-Sep-24
Shear ID: 264119
Test No: 621117


Animal and Sample Description

Animal Name: RED GRANITES AFTERSHOCK BY ALYC
Registry #: 35595410
Breed: Huacaya
Sex: Male
Colour: 306 - Dark Rose Grey

Date of Birth (Age): 19-Apr-23
Sample Location: GRID
Sample Date: 31-May-24
Previous Shear Date: 3-Jun-23
Total Fleece Wt (lbs): 4.4375

Laboratory Data

Mean Fiber Diameter:	16.4 microns	Mean Staple Length:	100 mm
Standard Deviation:	4.1 microns	Length Standard Deviation:	2.8 mm
Coefficient of Variation:	24.8 %	Length Coefficient of Variation:	2.8 %
Spin Fineness:	16.5 microns	Mean Curvature:	59.2 deg/mm
Fibers Greater Than 30 microns:	0.5 %	SD Curvature:	42.0 deg/mm
Comfort Factor:	99.5 %		



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilmorie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com