



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Red Granites Ranch
1021 Red Granite Ranch Rd, Livermore
CO 80536, US

Date: 26-Sep-24
Shear ID: 264221
Test No: 621215


Animal and Sample Description

Animal Name: RED GRANITES OLITA
Registry #: 35577744
Breed: Huacaya
Sex: Female
Colour: 202 - Light Fawn

Date of Birth (Age): 1-Apr-23
Sample Location: GRID
Sample Date: 31-May-24
Previous Shear Date: 3-Jun-23
Total Fleece Wt (lbs): 4.5625

Laboratory Data

Mean Fiber Diameter:	14.8 microns	Mean Staple Length:	101 mm
Standard Deviation:	3.5 microns	Length Standard Deviation:	3.1 mm
Coefficient of Variation:	24.0 %	Length Coefficient of Variation:	3.1 %
Spin Fineness:	14.8 microns	Mean Curvature:	60.8 deg/mm
Fibers Greater Than 30 microns:	0.3 %	SD Curvature:	41.5 deg/mm
Comfort Factor:	99.7 %	Medullated Fibers:	6.0 %



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilmorie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com