



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Red Granites Ranch
1021 Red Granite Ranch Rd, Livermore
CO 80536, US

Date: 25-Sep-24
Shear ID: 264151
Test No: 621149


Animal and Sample Description

Animal Name: RED GRANITES CAPER
Registry #: 36291144
Breed: Huacaya
Sex: Female
Colour: 301 - Medium Brown

Date of Birth (Age): 7-Jun-23
Sample Location: GRID
Sample Date: 31-May-24
Previous Shear Date: 15-Aug-23
Total Fleece Wt (lbs): 3.4375

Laboratory Data

Mean Fiber Diameter:	18.1 microns	Mean Staple Length:	91 mm
Standard Deviation:	4.0 microns	Length Standard Deviation:	3.2 mm
Coefficient of Variation:	22.4 %	Length Coefficient of Variation:	3.5 %
Spin Fineness:	17.8 microns	Mean Curvature:	48.9 deg/mm
Fibers Greater Than 30 microns:	1.4 %	SD Curvature:	40.0 deg/mm
Comfort Factor:	98.6 %		



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilmorie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com