



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Sunny Alpacas
9200 Spooner Creek Ln, Blaine
WA 98230, US

Date: 16-Aug-24
Shear ID: 269352
Test No: 619865


Animal and Sample Description

Animal Name: Sunny Andean BESTie
Registry #: 36156108
Breed: Huacaya
Sex: Female
Colour: 205 - Dark Fawn

Date of Birth (Age): 17-Jun-23
Sample Location: GRID
Sample Date: 11-Jun-24
Previous Shear Date: 15-Jul-23
Total Fleece Wt (lbs): 6.0

Laboratory Data

Mean Fiber Diameter:	18.9 microns	Mean Staple Length:	125 mm
Standard Deviation:	3.9 microns	Length Standard Deviation:	6.0 mm
Coefficient of Variation:	20.6 %	Length Coefficient of Variation:	4.8 %
Spin Fineness:	18.3 microns	Mean Curvature:	51.3 deg/mm
Fibers Greater Than 30 microns:	0.5 %	SD Curvature:	36.5 deg/mm
Comfort Factor:	99.5 %		



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilmorie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com