



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

DAWN REBECCA BEALS
9203 S Steels Rd
Prosser, WA 99350-7711 US

Date: 5-Aug-20
Shear ID: 200294
Test No: 198318


Animal and Sample Description

Animal Name: PacaPoo's Caramel Latte
Registry #: 35364030
Breed: Huacaya
Sex: Female
Colour: 202 - Light Fawn

Date of Birth (Age): 28-May-19
Sample Location: GRID
Sample Date: 25-Apr-20
Previous Shear Date: 8-Aug-19
Total Fleece Wt (lbs): 4.10

Laboratory Data

Mean Fiber Diameter:	24.6 microns	Mean Staple Length:	89 mm
Standard Deviation:	4.5 microns	Length Standard Deviation:	2.1 mm
Coefficient of Variation:	18.2 %	Length Coefficient of Variation:	2.3 %
Spin Fineness:	23.3 microns	Mean Curvature:	43.3 deg/mm
Fibers Greater Than 30 microns:	9.9 %	SD Curvature:	24.9 deg/mm
Comfort Factor:	90.1 %	Medullated Fibers:	%



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Jude Davidson
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilbirnie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: nz.wool.timaru@sgs.com Web: www.wooltesting.sgs.com