



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Spirit Fall Ranch
72 McNichols Rd, Cook
WA 98605, US

Date: 2-Oct-24
Shear ID: 266493
Test No: 621956

Animal and Sample Description


Animal Name: SFAR Jasmine
Registry #: 36120925
Breed: Huacaya
Sex: Female
Colour: Dark Fawn

Date of Birth (Age): 23-Sep-23
Sample Location: GRID
Sample Date: 27-Apr-24
Previous Shear Date: 4-Oct-23
Total Fleece Wt (lbs): 2.4

Laboratory Data

Mean Fiber Diameter: 16.5 microns
Standard Deviation: 4.0 microns
Coefficient of Variation: 24.2 %
Spin Fineness: 16.5 microns
Fibers Greater Than 30 microns: 0.6 %
Comfort Factor: 99.4 %

Mean Staple Length: 76 mm
Length Standard Deviation: 2.1 mm
Length Coefficient of Variation: 2.7 %
Mean Curvature: 59.6 deg/mm
SD Curvature: 39.0 deg/mm



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilmorie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com