


HEART

AFD: 22.1 μ
SD: 4.6 μ
CV: 20.8 %
CF: 94.7 %
Curve: 49.0 Dg/mm
Min: 21.1 μ
Max: 23.2 μ
Staple: 110.0 mm

% of Fibers



Alpaca Fiber Testing USA

Fiber Diameter (microns)

HEART

AFD: 22.1 μ
SD: 4.6 μ
CV: 20.8 %
CF: 94.7 %
Curve: 49.0 Dg/mm
Min: 21.1 μ
Max: 23.2 μ
Staple: 110.0 mm

