


AFD: 18.5 μ
SD: 3.4 μ
CV: 18.2 %
CF: 99.7 %
Curve: 48.0 Dg/mm
Min: 17.1 μ
Max: 19.6 μ
Staple: 110.0 mm

% of Fibers



Alpaca Fiber Testing USA

Fiber Diameter (microns)

HYDRA

AFD: 18.5 μ
SD: 3.4 μ
CV: 18.2 %
CF: 99.7 %
Curve: 48.0 Dg/mm
Min: 17.1 μ
Max: 19.6 μ
Staple: 110.0 mm

