


# CYPHER

**AFD:** 16.2  $\mu$   
**SD:** 3.1  $\mu$   
**CV:** 18.9 %  
**CF:** 100.0 %  
**Curve:** 52.5 Dg/mm  
**Min:** 15.3  $\mu$   
**Max:** 17.8  $\mu$   
**Staple:** 110.0 mm

% of Fibers



Alpaca Fiber Testing USA

Fiber Diameter (microns)

# CYPHER

**AFD:** 16.2  $\mu$   
**SD:** 3.1  $\mu$   
**CV:** 18.9 %  
**CF:** 100.0 %  
**Curve:** 52.5 Dg/mm  
**Min:** 15.3  $\mu$   
**Max:** 17.8  $\mu$   
**Staple:** 110.0 mm

