



## Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Triple Diamonds Alpaca Ranch  
3275 E Schafer Rd. Howell  
MI 48843-9422, US

Date: 28-Oct-22  
Shear ID: 242461  
Test No: 610649


### Animal and Sample Description

Animal Name: 3Dr Beau's Shimmer  
Registry #: 36144594  
Breed: Huacaya  
Sex: Female  
Colour: 201 - Beige

Date of Birth (Age): 29-Apr-21  
Sample Location: GRID  
Sample Date: 7-May-22  
Previous Shear Date: 6-Jun-21  
Total Fleece Wt (lbs): 4.50

### Laboratory Data

Mean Fiber Diameter:	16.6 microns	Mean Staple Length:	107 mm
Standard Deviation:	3.5 microns	Length Standard Deviation:	5.3 mm
Coefficient of Variation:	21.1 %	Length Coefficient of Variation:	4.9 %
Spin Fineness:	16.1 microns	Mean Curvature:	53.6 deg/mm
Fibers Greater Than 30 microns:	0.5 %	SD Curvature:	21.4 deg/mm
Comfort Factor:	99.5 %	Medullated Fibers:	3.5 %



### Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear  
Business Manager

Ioasa Kosena  
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilmorie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: [WoolOnline@sgs.com](mailto:WoolOnline@sgs.com) Web: [www.wooltesting.sgs.com](http://www.wooltesting.sgs.com)