



**Optical Fiber Diameter Analyser (OFDA100)  
Micron Test Report**

Briarwood Acres  
4150 Briarwood NW St, Salem  
OR 97304, US

Date: 17-Jul-24  
Shear ID: 263273  
Test No: 619266


**Animal and Sample Description**

Animal Name: SSKY ACCOYO CHASIDY  
Registry #: 30831155  
Breed: Suri  
Sex: Female  
Colour: 204 - Medium Fawn

Date of Birth (Age): 3-Jun-11  
Sample Location: GRID  
Sample Date: 21-May-24  
Previous Shear Date: 23-May-23  
Total Fleece Wt (lbs): 3.50

**Laboratory Data**

Mean Fiber Diameter:	26.2 microns	Mean Staple Length:	104 mm
Standard Deviation:	6.5 microns	Length Standard Deviation:	0.9 mm
Coefficient of Variation:	24.8 %	Length Coefficient of Variation:	0.9 %
Spin Fineness:	26.4 microns	Mean Curvature:	22.9 deg/mm
Fibers Greater Than 30 microns:	16.5 %	SD Curvature:	25.4 deg/mm
Comfort Factor:	83.5 %		



**Test Performed According to Method AS/NZS 4492.5:2000**

Jeremy Wear  
Business Manager

Ioasa Kosena  
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below  
SGS NZ LTD - 48 Kemp Street, Kilbirnie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: [WoolOnline@sgs.com](mailto:WoolOnline@sgs.com) Web: [www.wooltesting.sgs.com](http://www.wooltesting.sgs.com)