



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Brianwood Acres
4150 Brianwood NW St, Salem
OR 97304, US

Date: 17-Jul-24
Shear ID: 263275
Test No: 619268


Animal and Sample Description

Animal Name: TALENT'S TOSCANINI OF 2POINTFARM
Registry #: 35179979
Breed: Suri
Sex: Male
Colour: 100 - White

Date of Birth (Age): 12-Jun-17
Sample Location: GRID
Sample Date: 21-May-24
Previous Shear Date: 23-May-23
Total Fleece Wt (lbs): 7.4375

Laboratory Data

Mean Fiber Diameter:	36.8 microns	Mean Staple Length:	140 mm
Standard Deviation:	9.5 microns	Length Standard Deviation:	4.5 mm
Coefficient of Variation:	25.7 %	Length Coefficient of Variation:	3.2 %
Spin Fineness:	37.4 microns	Mean Curvature:	22.8 deg/mm
Fibers Greater Than 30 microns:	75.6 %	SD Curvature:	24.5 deg/mm
Comfort Factor:	24.4 %	Medullated Fibers:	75.4 %



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilmire 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com