


AFD: 20.5 μ
SD: 4.8 μ
CV: 23.3 %
CF: 96.6 %
Curve: 32.5 Dg/mm
Min: 17.0 μ
Max: 23.6 μ
Staple: 140.0 mm

% of Fibers



Alpaca Fiber Testing USA

Fiber Diameter (microns)

JENNA

AFD: 20.5 μ
SD: 4.8 μ
CV: 23.3 %
CF: 96.6 %
Curve: 32.5 Dg/mm
Min: 17.0 μ
Max: 23.6 μ
Staple: 140.0 mm

