



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Ariya Alpacas Inc
411 Brill Road
West Bolton QC, J0E 2T0 Canada

Date: 28-Jul-20
Shear ID:
Test No: 200866


Animal and Sample Description

Animal Name: Snowmass Everlasting Highlander XX
Registry #: 35263432
Breed: Huacaya
Sex: Male
Colour: med fawn

Date of Birth (Age):
Sample Location: GRID
Sample Date:
Previous Shear Date:
Total Fleece Wt (lbs): 0.00

Laboratory Data

Mean Fiber Diameter:	18.6 microns	Mean Staple Length:	87 mm
Standard Deviation:	4.1 microns	Length Standard Deviation:	2.9 mm
Coefficient of Variation:	22.1 %	Length Coefficient of Variation:	3.3 %
Spin Fineness:	18.3 microns	Mean Curvature:	66.0 deg/mm
Fibers Greater Than 30 microns:	1.2 %	SD Curvature:	33.8 deg/mm
Comfort Factor:	98.8 %	Medullated Fibers:	%



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Jude Davidson
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilbirnie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: nz.wool.timaru@sgs.com Web: www.wooltesting.sgs.com