


PRINCETON FROM MARS

AFD: 20.5 μ
SD: 4.6 μ
CV: 22.5 %
CF: 96.4 %
Curve: 33.9 Dg/mm
Min: 17.4 μ
Max: 22.8 μ
Staple: 90.0 mm

% of Fibers

Alpaca Fiber Testing USA



Fiber Diameter (microns)

PRINCETON FROM MARS

AFD: 20.5 μ
SD: 4.6 μ
CV: 22.5 %
CF: 96.4 %
Curve: 33.9 Dg/mm
Min: 17.4 μ
Max: 22.8 μ
Staple: 90.0 mm

