


WIND'S IDA

AFD: 24.6 μ
SD: 5.2 μ
CV: 21.1 %
CF: 86.7 %
Curve: 35.6 Dg/mm
Min: 22.7 μ
Max: 26.8 μ
Staple: 65.0 mm

% of Fibers



Alpaca Fiber Testing USA

Fiber Diameter (microns)

WIND'S IDA

AFD: 24.6 μ
SD: 5.2 μ
CV: 21.1 %
CF: 86.7 %
Curve: 35.6 Dg/mm
Min: 22.7 μ
Max: 26.8 μ
Staple: 65.0 mm

