


# WINDY'S MALVINA

**AFD:** 24.0  $\mu$   
**SD:** 5.0  $\mu$   
**CV:** 20.7 %  
**CF:** 90.2 %  
**Curve:** 41.6 Dg/mm  
**Min:** 23.1  $\mu$   
**Max:** 25.7  $\mu$   
**Staple:** 65.0 mm

% of Fibers

*Alpaca Fiber Testing USA*



# WINDY'S MALVINA

**AFD:** 24.0  $\mu$   
**SD:** 5.0  $\mu$   
**CV:** 20.7 %  
**CF:** 90.2 %  
**Curve:** 41.6 Dg/mm  
**Min:** 23.1  $\mu$   
**Max:** 25.7  $\mu$   
**Staple:** 65.0 mm

