


WINDY'S SIMON

AFD: 23.6 μ
SD: 5.1 μ
CV: 21.5 %
CF: 90.0 %
Curve: 29.9 Dg/mm
Min: 21.4 μ
Max: 24.7 μ
Staple: 75.0 mm

% of Fibers




Alpaca Fiber Testing USA

Fiber Diameter (microns)

WINDY'S SIMON

AFD: 23.6 μ
SD: 5.1 μ
CV: 21.5 %
CF: 90.0 %
Curve: 29.9 Dg/mm
Min: 21.4 μ
Max: 24.7 μ
Staple: 75.0 mm



Alpaca Fiber Testing USA