


WINDY'S TOBAN

AFD: 21.9 μ
SD: 4.3 μ
CV: 19.8 %
CF: 96.1 %
Curve: 28.9 Dg/mm
Min: 20.3 μ
Max: 23.4 μ
Staple: 95.0 mm

% of Fibers



Alpaca Fiber Testing USA

Fiber Diameter (microns)

WINDY'S TOBAN

AFD: 21.9 μ
SD: 4.3 μ
CV: 19.8 %
CF: 96.1 %
Curve: 28.9 Dg/mm
Min: 20.3 μ
Max: 23.4 μ
Staple: 95.0 mm

