



# WINDY'S REYNOLDS

**AFD:** 18.1  $\mu$   
**SD:** 4.0  $\mu$   
**CV:** 21.9 %  
**CF:** 99.3 %  
**Curve:** 35.7 Dg/mm  
**Min:** 16.5  $\mu$   
**Max:** 20.4  $\mu$   
**Staple:** 75.0 mm



# WINDY'S REYNOLDS

**AFD:** 18.1  $\mu$   
**SD:** 4.0  $\mu$   
**CV:** 21.9 %  
**CF:** 99.3 %  
**Curve:** 35.7 Dg/mm  
**Min:** 16.5  $\mu$   
**Max:** 20.4  $\mu$   
**Staple:** 75.0 mm



*Alpaca Fiber Testing USA*