


RAYNAY'S DRE

AFD: 17.9 μ
SD: 4.8 μ
CV: 26.6 %
CF: 99.5 %
Curve: 13.2 Dg/mm
Min: 14.9 μ
Max: 22.5 μ
Staple: 120.0 mm

% of Fibers



Alpaca Fiber Testing USA

Fiber Diameter (microns)

RAYNAY'S DRE

AFD: 17.9 μ
SD: 4.8 μ
CV: 26.6 %
CF: 99.5 %
Curve: 13.2 Dg/mm
Min: 14.9 μ
Max: 22.5 μ
Staple: 120.0 mm

