


# GRAND RIVER JASMIN

**AFD:** 27.0  $\mu$   
**SD:** 5.5  $\mu$   
**CV:** 20.4 %  
**CF:** 77.6 %  
**Curve:** 42.4 Dg/mm  
**Min:** 26.2  $\mu$   
**Max:** 28.9  $\mu$   
**Staple:** 60.0 mm


% of Fibers



Fiber Diameter (microns)

# GRAND RIVER JASMIN

**AFD:** 27.0  $\mu$   
**SD:** 5.5  $\mu$   
**CV:** 20.4 %  
**CF:** 77.6 %  
**Curve:** 42.4 Dg/mm  
**Min:** 26.2  $\mu$   
**Max:** 28.9  $\mu$   
**Staple:** 60.0 mm



*Alpaca Fiber Testing USA*