



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Briarwood Acres
4150 Briarwood NW St, Salem
OR 97304, US

Date: 17-Jul-24
Shear ID: 263268
Test No: 619261


Animal and Sample Description

Animal Name: Briarwood's Copper by Bravo
Registry #: 35523574
Breed: Suri
Sex: Male
Colour: 205 - Dark Fawn

Date of Birth (Age): 2-Jun-19
Sample Location: GRID
Sample Date: 21-May-24
Previous Shear Date: 23-May-23
Total Fleece Wt (lbs): 9.3125

Laboratory Data

Mean Fiber Diameter:	34.8 microns	Mean Staple Length:	161 mm
Standard Deviation:	7.4 microns	Length Standard Deviation:	1.1 mm
Coefficient of Variation:	21.2 %	Length Coefficient of Variation:	0.7 %
Spin Fineness:	34.0 microns	Mean Curvature:	23.0 deg/mm
Fibers Greater Than 30 microns:	73.7 %	SD Curvature:	26.2 deg/mm
Comfort Factor:	26.3 %		



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilmirrie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com